

Cloisite® 25A

# Attachment H

Page 1 of 2

## CLOISITE® 25A

### TYPICAL PHYSICAL PROPERTIES BULLETIN

**Description:**

Cloisite® 25A is a natural montmorillonite modified with a quaternary ammonium salt.




Commercially available in the USA only

**Designed Used:**

Cloisite® 25A is an additive for plastics to improve various plastic physical properties, such as reinforcement, HDT, CLTE and barrier.

**Typical Properties:**

Treatment/Properties:	Organic Modifier (1)	Modifier Concentration	% Moisture	% Weight Loss on Ignition
Cloisite® 25A	2MHTL8	95 mcg/100g clay	< 2%	34%



Where HT is Hydrogenated Tallow (~65% C18; ~30% C16; ~5% C14)  
Anion: methyl sulfate

(1) 2MHTL8: dimethyl, hydrogenated tallow, 2-ethylhexyl quaternary ammonium

**Typical Dry Particle Sizes: (microns, by volume)**

10% less than:	50% less than:	90% less than:
2μ	6μ	13μ

Color: Off White

**Density:**

Loose Bulk, lbs/ft <sup>3</sup>	Packed Bulk, lbs/ft <sup>3</sup>	Specific Gravity, g/cc
12.08	20.48	1.87

Cloisite® 25A

Page 2 of 2

X Ray Results:  $d_{001} = 18.6 \text{ \AA}$

**Southern Clay Products, Inc.** 1212 Church Street Gonzales, Texas 78629 USA  
Phone: (830) 672-2891 Fax: (830) 672-1903 US Toll Free: 1-800-324-2891